



# 7808 E - 3M TT3 MS PET 50-310E-90WG

## Thermal Transfer Polyester Label Material

<b>Issued</b>	:	<b>July 2001</b>
<b>Supersedes</b>	:	<b>February 2001</b>

---

**Physical Properties**  
Not for specification purposes  
(Calipers are nominal values)

<b>Facestock</b>	56 micron Matte Silver polyester
<b>Adhesive</b>	20 micron #310 E Acrylic
<b>Liner</b>	77 micron, 90 g/m <sup>2</sup> White Densified Glassine
<b>Shelf Life</b>	24 months from date of manufacture of product when properly stored between 22°C and 50% relative humidity.

---

**Features:**

- Facestock is treated with a high durability matte top coat capable of withstanding harsh chemicals encountered in both automotive and electronic environments.
- Matte topcoat provides the advantages of matte coating combined with a surface that is smooth enough for thermal transfer printing. Resin ribbons are recommended for optimum durability. The matte coating is extremely resistant to degradation from scuffing, chemicals, moisture, and wide temperature fluctuations. When printed with specified ribbons, thermal transfer image remains legible after rubbing with Brake Fluid. The topcoat also provides improved ink anchorage for traditional forms of press printing.
- 310 E is a firm adhesive, which resists oozing and provides high strength on a variety of surfaces including high surface energy (HSE) plastics and metals. It additionally has improved chemical and U.V resistance.
- 90 g/m<sup>2</sup> densified glassine liner assures consistent die cutting.
- UL and CUL listings are pending

---

**Application Ideas:**

- Barcode labels and rating plates in automotive underbonnet applications.
- Property identification and asset labelling in harsh environments.
- Property identification and asset labelling.
- Warning, instruction, and service labels for durable goods.
- Nameplates for durable goods.

**Performance Characteristics**  
 Not for specification purposes

	<b>Adhesion</b>		<b>90°Peel Adhesion, Test procedure FTM 2</b>	
			<b>Initial (20 Minute Dwell/RT)</b>	
			<b>Ultimate Adhesion 72 Hours Dwell at Maximum UL Temperature rating</b>	
	<b>N/10mm</b>	<b>Oz/In</b>	<b>N/10mm</b>	<b>Oz/In</b>
<b>Aluminium</b>	3.1	28	6.4	58
<b>Stainless Steel</b>	4.7	43	6.8	62
<b>Phenolic</b>	3.1	28	4.7	43
<b>ABS</b>	3.4	31	3.2	29
<b>Polycarbonate</b>	2.5	23	3.1	28
<b>Polystyrene</b>	3.7	34	4.5	41
<b>Polypropylene</b>	0.5	4.6	1.8	16
<b>HD Polyethylene</b>	1.8	16	3.2	29
<b>LD Polyethylene</b>	0.9	8.2	1.3	12
<b>Powder Coating</b>	3.7	34	6.4	31

<b>Surface</b>	<b>Conditioned for 3 Days at - 40°C</b>	
	<b>90° Peel</b>	
	<b>N/10mm</b>	<b>Oz/In</b>
<b>Aluminium</b>	2.8	25
<b>Stainless Steel</b>	5.9	54
<b>Phenolic</b>	4.0	36
<b>ABS</b>	4.6	42
<b>Polycarbonate</b>	3.3	42
<b>Polystyrene</b>	4.5	41
<b>Polypropylene</b>	1.1	10
<b>HD Polyethylene</b>	2.0	18
<b>LD Polyethylene</b>	1.3	12
<b>Powder Coating</b>	3.3	30

**Performance Characteristics Contd.**  
 Not for specification purposes

	<b>180°Peel Adhesion, Test procedure FTM 1</b>			
	<b>Initial (20 Minute Dwell/RT)</b>		<b>Ultimate Adhesion 72 Hours Dwell at Maximum UL Temperature rating</b>	
	<b>N/10mm</b>	<b>Oz/In</b>	<b>N/10mm</b>	<b>Oz/In</b>
<b>Aluminium</b>	4.2	38	6.7	61
<b>Stainless Steel</b>	4.5	41	8.7	80
<b>Phenolic</b>	4.8	44	8.7	80
<b>ABS</b>	5.2	47	6.0	55
<b>Polycarbonate</b>	5.1	46	4.2	38
<b>Polystyrene</b>	4.8	44	4.8	44
<b>Polypropylene</b>	0.4	3.6	3.1	28
<b>HD Polyethylene</b>	0.4	3.6	3.0	27
<b>LD Polyethylene</b>	0.4	3.6	0.8	7.5

	<b>Conditioned for 3 Days at - 40°C</b>	
<b>Surface</b>	<b>180° Peel (FTM 1)</b>	
	<b>N/10mm</b>	<b>Oz/In</b>
<b>Aluminium</b>	4.7	43
<b>Stainless Steel</b>	7.0	64
<b>Phenolic</b>	5.0	46
<b>ABS</b>	4.9	45
<b>Polycarbonate</b>	5.8	53
<b>Polystyrene</b>	4.8	44
<b>Polypropylene</b>	0.6	5.5
<b>HD Polyethylene</b>	0.4	3.6
<b>LD Polyethylene</b>	0.4	3.6

<b>Liner Release</b>	<b>FTM 3 180° Removal of Liner from Facestock</b>		
	<b>Rate of Removal</b>	<b>N/10mm</b>	<b>Gms/50mm Width</b>
		2.3 m / min	0.025

<b>Environmental Performance</b>	The properties defined are based on four hour immersions at room temperature 22°C unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 90° peel angle (FTM 2 at 305 mm/min).				
<b>Chemical Resistance</b>	<b>Adhesion to Stainless Steel</b>			<b>Appearance</b>	<b>Edge Penetration</b>
<b>Chemical</b>	<b>N/10mm</b>	<b>Oz/In</b>	<b>% Change</b>	<b>Visual</b>	<b>Millimetres</b>
<b>Isopropyl Alcohol</b>	5.4	49	90	No change	1
<b>Detergent (1% Alconox®*)</b>	5.5	51	104	No change	1
<b>Engine Oil (10W30) @ 250°F (121°C)</b>	5.7	52	106	No change	1
<b>Water for 48 hours</b>	5.7	52	106	No change	0
<b>pH 4</b>	5.8	53	107	No change	0
<b>PH10</b>	5.8	53	107	No change	0
<b>Toluene</b>	3.1	28	57	Topcoat Damaged	5.0
<b>Acetone</b>	3.0	27	56	Topcoat Damaged	6.0
<b>Brake Fluid</b>	5.3	48	98	No Change	1
<b>Gasoline</b>	3.8	35	70	No change	5.0
<b>Diesel Fuel</b>	4.6	42	85	No change	0
<b>Naphtha</b>	3.2	29	59	No change	3.0
<b>Hydraulic Fluid</b>	5.6	51	103	No change	0

<b>Temperature Resistance</b>	149°C for 24 hours:	no significant visual change 0.7% MD shrinkage 0.9% CD shrinkage
	-40°C for 3 days:	no significant visual change
<b>Humidity Resistance</b>	24 hours at 38°C and 100% relative humidity	no significant changes in appearance or adhesion

## Agency Listing Information

### Thermal Transfer Printing:

Printer: UL no longer requires evaluation and listing of specific printers.

Armor: AXR-7; AXR-7+  
Ricoh™: B110C  
Sony™: TR 4070  
Keymax Alpha

### Press Inks:

For details of inks compatible with this labelstock that meet the requirements of both UL and CUL, please contact your local technical service engineer.

## Processing

### Printing:

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is printable by all standard roll processing methods including flexography, hot stamp, letterpress, and screen printing.

### Die Cutting:

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

### Packaging:

Finished labels should be stored in plastic bags.

---

## Special Considerations

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.

**NOTE:** When using solvents, read and follow the manufacturer's precautions and directions for use.

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 5°C can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

\* Trademarks listed are the property of their respective owners



## Tapes & Adhesives Group

© 3M United Kingdom PLC 2001

3M United Kingdom PLC  
3M House, PO Box 1,  
Market Place,  
Bracknell, Berkshire,  
RG12 1JU

Product Information :  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509