



7876EC 3M TT2 GC PET 50-350E/46-65DWG

Thermal Transfer Polyester Label Material

Provisional Product Data Sheet

Issued : **June 2004**
(Provisional)
Supersedes : **September 2002**
(Provisional)

Physical Properties
Not for specification purposes
(Calipers are nominal values)

Facestock	50 micron Gloss Clear polyester
Adhesive	46 micron #350 E Acrylic
Liner	56 micron, 62 g/m ² White Double sided Glassine
Shelf Life	24 months from date of manufacture of product when properly stored between 22°C and 50% relative humidity.

Features:

- Facestock is topcoated for thermal transfer printing. Resin ribbons are recommended for optimum durability. The topcoat also provides improved ink anchorage for traditional forms of press printing.
- 350 E 3M's most universal labelstock adhesive ,excellent adhesion, even on Low surface energy substrates combined with excellent temperature and chemical Resistance.
- 46 micron adhesive coat weight for excellent adhesion to textured surfaces
- 62 g/m² double sided glassine liner assures consistent die cutting, a backside release coating helps minimise label blocking.
- UL and cUL approved (File Number MH18072)

Application Ideas:

- Barcode labels and rating plates.
 - Property identification and asset labelling in harsh environments.
 - Warning, instruction, and service labels for durable goods.
 - Nameplates for durable, electronic and sporting goods.
-

Performance Characteristics
 Not for specification purposes

Adhesion	90°Peel Adhesion, Test procedure FTM 2			
	Initial (20 Minute Dwell/RT)		Ultimate Adhesion 72 Hours Dwell at 70° C	
	N/10mm	Oz/In	N/10mm	Oz/In
Aluminium	6.9	62	9.4	85
Stainless Steel	7.4	67	11.0	99
Phenolic	6.8	61	8.5	77
ABS	6.9	62	8.9	80
Polycarbonate	7.1	64	8.2	74
Polystyrene	6.9	62	7.5	68
Polypropylene	5.4	49	7.3	66
HD Polyethylene	4.1	37	5.1	46
LD Polyethylene	5.4	49	5.8	52
Powder Coating	6.3	57	9.2	83

Surface	Conditioned for 3 Days at - 40°C	
	90° Peel	
	N/10mm	Oz/In
Aluminium	6.3	57
Stainless Steel	8.0	72
Phenolic	6.8	61
ABS	7.5	68
Polycarbonate	7.4	67
Polystyrene	7.5	68
Polypropylene	6.4	58
HD Polyethylene	4.0	36
LD Polyethylene	5.1	46
Powder Coating	7.7	69

**Performance
 Characteristics Contd.**

Temperature Resistance	149°C for 24 hours:	no significant visual change 0.7% MD shrinkage 0.9% CD shrinkage
	-40°C for 3 days:	no significant visual change
Humidity Resistance	24 hours at 38°C and 100% relative humidity	no significant changes in appearance or adhesion

Environmental Performance	The properties defined are based on four hour immersions at room temperature 22°C unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 90° peel angle (FTM 2) at 305 mm/min.			
Chemical Resistance	Adhesion to Stainless Steel		Appearance	Edge Penetration
Chemical	N/10mm	Oz/In	Visual	Millimetres
Heptane	8.2	74	No change	3
Petrol	6.0	54	No change	3
Diesel	6.1	55	No change	1
SAE 15W40 Engine Oil	7.4	67	No change	0
Dot 4 Brake Fluid	7.8	70	No change	1
Screen Wash	7.1	64	No change	0
IPA	6.8	61	No change	1
Toluene	5.2	47	No change	4
MEK	5.4	49	No change	4
Lemsolve	6.2	56	No change	2
Teepol Detergent	7.4	67	No change	0
PH 4	6.6	59	No change	0
PH 10	7.2	65	No change	0
409 Solution	6.6	59	No change	0

Agency Listing Information

Thermal Transfer Printing:

UL and cUL approved with the following thermal transfer ribbons

Armor: AXR-8, AXR 600, AXR7+
Ricoh™: B120EC, B110CR
Sony™: TR4570
Zebra: 4800, 5095, 5100

Also UL approved with the following ribbons

Ricoh: B110CX
Astromed: RY, R5
Kurz: K501
Sony: TR5070

Processing

Printing:

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is printable by all standard roll-processing methods including flexography, hot stamp, letterpress, and screen-printing.

Die Cutting:

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing. Care should be taken when handling finished rolls to prevent telescoping. Please refer to Technical Service Bulletin Guide to converting 3M label Materials with 350E adhesive.

Packaging:

Finished labels should be stored in plastic bags.

Special Considerations

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.

NOTE: When using solvents, read and follow the manufacturer's precautions and directions for use.

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 5°C can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

* Trademarks listed are the property of their respective owners



Tapes & Adhesives Group

© 3M United Kingdom PLC 2004

3M United Kingdom PLC
3M Centre, Cain Road,
Bracknell, Berkshire,
RG12 8HT

Product Information :
Tel 0870 60 800 50
Fax 0870 60 700 99

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509