



7879EJ- 3M TT3 MS PET 75-350E/46-90DWG

Thermal Transfer Polyester Label Material

| | | |
|-------------------|---|-----------------------|
| Issued | : | September 2002 |
| Supersedes | : | February 2002 |

Physical Properties

Not for specification purposes
(Calipers are nominal values)

| | |
|-------------------|--|
| Facestock | 81 Micron Matte Silver polyester |
| Adhesive | 46 micron #350 E Acrylic |
| Liner | 77 micron, 90 g/m ² White Double sided Glassine |
| Shelf Life | 24 months from date of manufacture of product when properly stored between 22°C and 50% relative humidity. |

Features:

- TT3 Matte topcoat provides the advantages of matte coating combined with a surface that is smooth enough for thermal transfer printing. High abrasion resistance combined with excellent chemical resistance of the thermal transfer image, even against aggressive chemicals like Brake fluid. Resin ribbons are recommended for optimum durability. The topcoat also provides improved ink anchorage for traditional forms of press printing
- 350 E 3M's most universal labelstock adhesive ,excellent adhesion, even on Low surface energy substrates combined with excellent temperature and chemical Resistance.
- 46 micron adhesive coat weight for excellent adhesion to textured surfaces
- 90 g/m² double sided glassine liner assures consistent die cutting, a backside release coating helps minimise label blocking.
- UL and cUL approved as 7879E (File No. Mh18072)

Application Ideas:

- Barcode labels and rating plates.
- Property identification and asset labelling in harsh environments.
- Warning, instruction, and service labels for durable goods.
- Nameplates for durable, electronic and sporting goods.

Performance Characteristics
 Not for specification purposes

| Adhesion | 90°Peel Adhesion, Test procedure FTM 2 | | | |
|-----------------|--|-------|---|-------|
| | Initial (20 Minute Dwell/RT) | | Ultimate Adhesion 72 Hours Dwell at 70° C | |
| | N/10mm | Oz/In | N/10mm | Oz/In |
| Aluminium | 6.9 | 62 | 9.4 | 85 |
| Stainless Steel | 7.4 | 67 | 11.0 | 99 |
| Phenolic | 6.8 | 61 | 8.5 | 77 |
| ABS | 6.9 | 62 | 8.9 | 80 |
| Polycarbonate | 7.1 | 64 | 8.2 | 74 |
| Polystyrene | 6.9 | 62 | 7.5 | 68 |
| Polypropylene | 5.4 | 49 | 7.3 | 66 |
| HD Polyethylene | 4.1 | 37 | 5.1 | 46 |
| LD Polyethylene | 5.4 | 49 | 5.8 | 52 |
| Powder Coating | 6.3 | 57 | 9.2 | 83 |

| Surface | Conditioned for 3 Days at - 40°C | |
|-----------------|----------------------------------|-------|
| | 90° Peel | |
| | N/10mm | Oz/In |
| Aluminium | 6.3 | 57 |
| Stainless Steel | 8.0 | 72 |
| Phenolic | 6.8 | 61 |
| ABS | 7.5 | 68 |
| Polycarbonate | 7.4 | 67 |
| Polystyrene | 7.5 | 68 |
| Polypropylene | 6.4 | 58 |
| HD Polyethylene | 4.0 | 36 |
| LD Polyethylene | 5.1 | 46 |
| Powder Coating | 7.7 | 69 |

**Performance
 Characteristics Contd.**

| | | |
|-------------------------------|---|--|
| Temperature Resistance | 149°C for 24 hours: | no significant visual change 0.7% MD shrinkage 0.9% CD shrinkage |
| | -40°C for 3 days: | no significant visual change |
| Humidity Resistance | 24 hours at 38°C and 100% relative humidity | no significant changes in appearance or adhesion |

| | | | | |
|----------------------------------|--|--------------|-------------------|-------------------------|
| Environmental Performance | The properties defined are based on four hour immersions at room temperature 22°C unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 90° peel angle (FTM 2) at 305 mm/min. | | | |
| Chemical Resistance | Adhesion to Stainless Steel | | Appearance | Edge Penetration |
| Chemical | N/10mm | Oz/In | Visual | Millimetres |
| Heptane | 8.2 | 74 | No change | 3 |
| Petrol | 6.0 | 54 | No change | 3 |
| Diesel | 6.1 | 55 | No change | 1 |
| SAE 15W40 Engine Oil | 7.4 | 67 | No change | 0 |
| Dot 4 Brake Fluid | 7.8 | 70 | No change | 1 |
| Screen Wash | 7.1 | 64 | No change | 0 |
| IPA | 6.8 | 61 | No change | 1 |
| Toluene | 5.2 | 47 | No change | 4 |
| MEK | 5.4 | 49 | No change | 4 |
| Lemsolve | 6.2 | 56 | No change | 2 |
| Teepol Detergent | 7.4 | 67 | No change | 0 |
| PH 4 | 6.6 | 59 | No change | 0 |
| PH 10 | 7.2 | 65 | No change | 0 |
| 409 Solution | 6.6 | 59 | No change | 0 |

Thermal Transfer Printing

Suitable for thermal transfer printing with the following thermal transfer ribbons

Armor AXR 7+
Armor: AXR 8
Ricoh™: B110 CX
Sony™: TR 5070
Astromed R5, RY
Kurz 501

Processing

Printing:

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is printable by all standard roll-processing methods including flexography, hot stamp, letterpress, and screen-printing.

Die Cutting:

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing. Care should be taken when handling finished rolls to prevent telescoping. Please refer to Technical Service Bulletin Guide to converting 3M label Materials with 350E adhesive.

Packaging:

Finished labels should be stored in plastic bags.

Special Considerations

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.

NOTE: When using solvents, read and follow the manufacturer's precautions and directions for use.

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 5°C can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

* Trademarks listed are the property of their respective owners



Tapes & Adhesives Group

© 3M United Kingdom PLC 2002

3M United Kingdom PLC
3M Centre, Cain Road,
Bracknell, Berkshire,
RG12 8HT

Product Information :
Tel 0870 60 800 50
Fax 0870 60 700 99

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509