

## PRODUCT DATA SHEET



# Avery® FasCal® 400 Supertack

issued: 01/07/2002

### Introduction

FasCal 400 Supertack is a screenprint film for shortterm applications. The special adhesive provides good adhesion of the film to polyethylene, polypropylene and other critical substrate materials.

### Description

Facefilms: 100 micron, monomerically plasticised, white glossy film  
Adhesive: permanent, high tack, acrylic based  
Liner : one side coated kraft liner

### Features

FasCal 400 Supertack features excellent conversion and printing characteristics: it can be screenprinted with most common screen inks for self-adhesive films. FasCal 400 Supertack has excellent layflatness and dimensional stability properties to ensure high output and exact registered prints.  
FasCal 400 Supertack has excellent outdoor exposure properties.  
For screen ink recommendations: consult Avery Technical Bulletin No. 2.2.

### Recommendations for use

- Labels and stickers
- Short term outdoor advertising
- Posters, panels and signs at exhibitions
- Public transport advertising
- Labels and stickers
- Point of sale promotions



[www.averygraphics.com](http://www.averygraphics.com)

Graphics Division  
Rijndijk 86, P.O. Box 118  
2394 ZG Hazerswoude – The Netherlands  
Tel +31 71 3421500 – Fax +31 71 3421538

# PRODUCT CHARACTERISTICS

Avery® FasCal® 400 Supertack

## Physical properties

Features	Test method <sup>1</sup>	Results
Caliper, facefilm	ISO 534	100 micron
Gloss	ISO 2813, 20°	70 %
Dimensional stability	DIN 30646	0.5 mm. max
Adhesion, initial	FINAT FTM-1, stainless steel polyethylene	500 N/m 400 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel polyethylene	800 N/m 650 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Durability <sup>2</sup>	Vertical exposure	2 years

## Temperature range

Features	Results
Application temperature	Minimum: 0° C
Service temperature	-40° to +100° C

## Chemical properties

Features	Test method <sup>1</sup>	Results
Humidity resistance	120 hours exposure	No effect
Corrosion resistance	120 hours exposure	No contribution to corrosion
Water resistance	48 hours immersion	No effect
Solvent resistance	Applied to aluminium and	No effect exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.

### Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change.

### Warranty

Avery® branded materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give any guarantee, warranty, or make any representation contrary to the foregoing. All Avery® branded materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

### 1) Test methods

More information about our test methods can be found on our website.

### 2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.



www.averygraphics.com

Graphics Division  
Rijndijk 86, P.O. Box 118  
2394 ZG Hazerswoude – The Netherlands  
Tel +31 71 3421500 – Fax +31 71 3421538