

Product Construction Sheet

FLEXmark® PM 200 W TC-200 L-156 (1.0-1.1) 98PFW

GENERAL DESCRIPTION:

This is a top-coated white polyester film, coated with a permanent pressure sensitive acrylic adhesive and backed with a layflat release liner.

UL RECOGNITION:

This product is UL recognized for indoor use with occasional exposure to lubricating oil and water. For further information, please reference FLEXcon's UL file No MH10170 (N) or contact your FLEXcon Representative.

NOTE: This product is not intended to be used for fan-fold applications. L-156 is a soft adhesive and will have a tendency to ooze at 38 micron coat weight, customer must evaluate their conversion process and end-use application thoroughly.

PRODUCT DATA	VALUE	TEST METHOD
PHYSICAL PROPERTIES		
Thickness (micron)	Film	50 +/- 10 %
	Adhesive	25-28 +/- 3
	Liner	166 +/- 10 %
ASTM D 3652		
Dimensional Stability (%)	No shrinkage observed	On Al panel at 70°C for 24 hr.

ADHESION PROPERTIES**

Adhesion from (N/m)	Average	
Stainless Steel	792	FTM 1 (Modified for 72 hr dwell time)
Acrylic	1045	
Glass	825	
Expected Shear (Hours)	5	FTM 8
Tack (gm/sq cm)	420	ASTM D 2979

** For guidance only

This data is based on limited test results due to the custom nature of this product, not to be used for setting specifications.

EXPECTED EXTERIOR LIFE	Two years
SERVICE TEMPERATURE RANGE	-40°C to 150°C
MINIMUM APPLICATION TEMPERATURE	2°C
STORAGE STABILITY	Two years stored at 21°C and 50% RH

*FLEXmark is a trademark of FLEXcon Company, Inc.

08-08-2018

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.