



*Providing Solutions in Pressure Sensitive Films*

## Product Construction Sheet

FLEXmount™ DFM 200 WHITE V-660 120POLYC-9 V-660 98PFW

**GENERAL DESCRIPTION:**

This is a white polyester film coated on both sides with a high tack permanent pressure sensitive acrylic adhesive and backed on one side with an ultra smooth clear polyester release liner and on the other side with a lay-flat release liner.

PRODUCT DATA	VALUE	TEST METHOD
<b>PHYSICAL PROPERTIES</b>		
Thickness (micron)	120PolyC-9 Liner: 30 Adhesive: 22-25 Film: 50 Adhesive: 22-25 98PFW Liner: 166	+/- 10 % +/- 3 +/- 10 % +/- 3 +/- 10 %
		ASTM D 3652

**ADHESION PROPERTIES\*\***

Adhesion from (N/m)	Average	TEST METHOD
Stainless Steel	660	FTM 1 (Modified 72 hr dwell time)
Acrylic	781	
Glass	594	
Expected Shear (hours)	20	FTM 8
Tack (gm/sq cm)	550	ASTM D 2979

\*\* For guidance only

This data is based on limited test results due to the custom nature of this product, not to be used for setting specifications.

EXPECTED EXTERIOR LIFE	2 years
SERVICE TEMPERATURE RANGE	-40`C to 150`C
MINIMUM APPLICATION TEMPERATURE	10`C
STORAGE STABILITY	One year stored at 21`C and 50% RH

\* FLEXmount is a trademark of FLEXcon Company, Inc.

21/04/2006

**Product Performance and Suitability**

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.